



<b>60 DEGREE BUNSEN BURNER TEST FOR WIRE</b> 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)	Skandia, Inc. WO # 257440-13 Client PO 17458-N
Pic Wire & Cable N63 W22619 Main St. P.O. Box 330  Sussex WI 53089-0330	Doc ID: 60DEG-281146 Test Plan # Rev Technician Ryerson Rickey

**AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION**

Make: Stock	Model: N/A	Serial: N/A	Tail: N/A
-------------	------------	-------------	-----------

Conditioning Room Data:    Date In: 06/12/2013    Time In: 09:35                      Date Out: 06/13/2013    Time Out: 14:29

**SPECIMEN MATERIALS**

Part No: **S33141**  
 Pic Wire & Cable: Wire, Clear, REF.#: Lot 136278

Lot No    P4-6835

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.4	0.0
2	30	0.0	1.5	0.0
3	30	0.0	1.4	0.0
<b>Average:</b>		0.0	1.4	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

**Passed**     **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.

Jane Biberstein -FAA DER <b>WITNESS</b>		06/13/2013 <b>DATE</b>
--	--	---------------------------