

www.Skandiainc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)				Skandia, Inc. WO # 208203-10 Client PO Verbal	
Pic Wire & Cable N63 W22619 Main St. P.O. Box 330				Doc ID: 60DEG-216558 Test Plan # Rev	
Sussex WI 53089-0330					
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION					
Make: Stock		Model:N/A	Serial: N//	I: N/A Tail: N/A	
Conditioning Room Data: Date				Date Out: 01/15/2010 Time Out: 10:56	
SPECIMEN MATERIALS					
0-1	Flame Application	Flame Time	Burn I	Length Dr	rip Flame Time
Set	(seconds)	(seconds)	(seco	nds)	(seconds)
1	30	0.0		0.2	0.0
2	30	0.0		0.3	0.0
3	30	0.0		0.2	0.0
	Average:	0.0		0.2	0.0
60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling. Comments:					
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2006.					
Gary K. Palmer - FAA DER					
WITNESS				DATE	