



60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)		Skandia, Inc. WO # 278201-14 Client PO 18545-N	
Pic Wire & Cable N53 W24747 S. Corporate Circle Sussex WI 53089 USA		Doc ID: 60DEG-307721 Test Plan # Rev Project # Technician Rickey Ryerson	

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION

Make: Stock	Model: N/A	Serial: N/A	Tail: N/A
-------------	------------	-------------	-----------

Conditioning Room Data: Date In: 08/27/2014 Time In: 09:50 Date Out: 08/28/2014 Time Out: 11:35

SPECIMEN MATERIALS

Part No: **USB2624**
 Pic Wire & Cable.: Cable, White, 26/24AWG

Lot No 141741

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.2	0.0
2	30	0.0	1.2	0.0
3	30	0.0	1.3	0.0
Average:		0.0	1.2	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.
 Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

Passed **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.

Jane Biberstein -FAA DER	08/28/2014
WITNESS	DATE